

Test Report

No. SHAHG1001290001

Date: 12 Feb 2010

Page 1 of 3

SHANGHAI SECCO PETROCHEMICAL CO.,LTD
XIHE ROAD,SHANGHAI INDUSTRY PARK,SHANGHAI,P.R.CHINA

The following sample(s) was/were submitted and identified on behalf of the clients as : S1003 FAC0085

SGS Job No. : SHD201003428 - SH
Date of Sample Received : 09 Feb 2010
Testing Period : 09 Feb 2010 - 12 Feb 2010
Test Requested : Selected test(s) as requested by client.
Test Method : Please refer to next page(s).
Test Results : Please refer to next page(s).
Conclusion : The submitted translucent plastic particle sample said to be used for S1003 FAC0085 comply with the FDA Specifications for polypropylene used in contact with food for the food simulation solvent used.

Signed for and on behalf of
SGS-CSTC Ltd.



Hao Jinyu, Sandy
Lab Manager

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This document cannot be reproduced except in full, without prior approval of the Company.



Test Report

No. SHAHG1001290001

Date: 12 Feb 2010

Page 2 of 3

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description
1	SHA10-012900.001	Translucent plastic particle

FDA 21 CFR 177.1520

Test Requested : As specified for client, for compliance with the Food and Drug Administration Regulations for polypropylene used in contact with food.

Test Method : As specified in FDA 21 CFR 177.1520.

Test Item(s)	Limit	001
Extractable fraction in n-hexane at reflux temperature,w/w%	6.4	0.7
Density at 23°C, g/ cm ³	0.880-0.913	0.901
Melting_point,°C*	160-180	165
Extractable fraction in xylene at 25°C, W/W %	9.8	2.1

Notes :

- (1) * These tests were subcontracted to SGS-SH MATERIAL LAB.

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This document cannot be reproduced except in full, without prior approval of the Company.

