

RAMAPET N1 (S)

Sales Specification Polyethylene Terephthalate (PET) Resin

Property	Unit	Test method	RAMAPET N1 (S) value
Intrinsic Viscosity	dl/g	SKEU-01-BB105	0.80 ± 0.02
Acetaldehyde	ppm	SKEU-01-BB107	Max 1
Colour L*	-	SKEU-01-BB101	Min 82
Colour a*	-	SKEU-01-BB101	-2.5 to -0.5
Colour b*	-	SKEU-01-BB101	-3 to 0
Pellet weight	Pieces/gram	SKEU-01-BB106	75 ± 10
Fines	Wt%	SKEU-01-BB109	Max 0.05

25 March 2011

Neither UAB Indorama Polymers Europe, UAB Orion Global PET, Indorama Polymers Poland Sp z o.o. nor their marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.