

100% Post Consumer Prevented Ocean Plastic™ rHDPE Pellet



RHDPE Specifications – ZW16-POP-rHDPE-Natural-MFI-1

PRODUCT	VALUE	PARAMETERS
SOURCE	Post Consumer	
Tensile Strength	10-25	MPa
Elongation at Break	50-150	%
Izod Notched Impact Strength	13-20	KJ/m ²
COLOUR	Natural	Visual
PARTICLE FORM	Spherical	
BULK DENSITY	935-980	KG / M ³
Melt Flow Rate (MFR)	0.9-1.6	g/10min
Melting Point	140-200	°C